



Coordinates of the laboratory

Eurofins Product Testing A/S Smedeskovvej 38 DK-8464 Galten Denmark

Report of N°392-2017-00199401: Formaldehyde reduction and emission

Identification of the samples

Internal Saint-Gobain reference: Novelio® Nature

Description of the sample: Glassfiber wallcoverings

Results

	1 day [μg/m³]	3 day [μg/m³]	7 day [μg/m³]
Empty chamber	150	130	140
Sample	79	68	71
Formaldehyde consumption	47%	48%	49%

Where Formaldehyde consumption is calculated as follow

$$FC = (C_{\rm in} - C_{\rm out})/C_{\rm in}$$

FC = formaldehyde consumption, %

Report	Designation	Signature	Date
Prepared by: Mrs Maria Pelle Madsen	Analytical chemist	Maryfelle	The 06/06/17
Checked by: Mrs Janne Rothmann Norup	Analytical Service manager	Janu R Nurp	The 06/06/17